

SHERWIN-WILLIAMS **CASENITE**

Washable Kalsomine



SHERWIN-WILLIAMS **CASENITE**

The Perfected Washable Kalsomine



Casenite is a washable water paint in dry powder form that is mixed with cool water after which it is ready for use. Casenite can be used on such surfaces as plaster, brick, tile, concrete, wood, wallboard, galvanized iron, etc.

Casenite requires no sizing, has good hiding and spreads easily. Flows out to a smooth velvety finish that doesn't streak. Retains its color and does not rub off on the clothes.

Casenite can be used with either brush or spray over old paint or paint can be applied over it if desired. It is an excellent undercoat under lacquer on new walls and ceilings and will be found very effective as a water stain killer on interior wall or ceiling surfaces.

A surface that has been Casenited should not be washed until it has dried from 30 to 60 days. Then finger marks, grime and dirt spots can be washed off with a dampened cloth or any mild soap suds without leaving any marks. Do not confuse scrubability with washability. Casenite can't be scrubbed but it can be washed or sponged lightly.

SHERWIN-WILLIAMS CASENITE

is preferred by experienced painters because —

One coat covers solidly over most surfaces.
It works easily under the brush, is self-sizing on new plaster.

Dries to touch in less than an hour.

Will not rub off.


Leaves no odor.

Flows easily and does not show laps or brush marks.

Can be applied on any solid surface, plaster, wood, wallboard, etc.

5 pounds covers 250-500 square feet.

CARE OF BRUSHES



Casenite is best applied by the professional with an S-W Dutch or Flat Kalsomine Brush. Satisfactory results can be secured, however, with any S-W Wall Brush. Do not allow the brushes to stand in the mixed paint over night or during the noon hour. Wash the brushes clean with cold water and hang up to dry with the bristles downward.

Good brushes can be ruined if this practice isn't followed.



C

IVORY 301

GRAY 305

CREAM 302

LIGHT BLUE 306

BUFF 303

PINK 307

TAUPE 304

GREEN 308

ALSO WHITE



PREPARATION OF SURFACE

Before applying, the surface to be coated must be put in condition to receive the finish.

All dirt and old coats of Kalsomine must be removed by applying warm water liberally and washing off with a sponge, and any loose oil paint previously applied must be scraped off. Lime wash is best removed by thoroughly soaking with vinegar, scrubbing with a stiff brush and washing off with clear water.

All cracks, nail holes and damaged places must be filled with Patching Plaster. Cracks should be cut out (made larger) by cutting in under the surface in dovetail fashion to prevent the filling from falling out.

MIXING DIRECTIONS

Pour five pounds CASENITE into one pint cold water in metal container. Add about two and one-half pints additional water and stir thoroughly until mixture is smooth and all lumps are broken up.

Let stand for about one-half hour to permit complete solution of ingredients, and thin with one to one and a half pints additional water, slightly more or less according to consistency desired for proper brushing on surface to be coated. CASENITE may be applied with spray or brush. Best brushing results will be obtained with the use of a large Wall or Kalsomine brush.

Mixed ready for use, CASENITE will cover with one coat from fifty to one hundred square feet to the pound, depending upon the surface conditions. Maximum coverage will be obtained on smooth plastered walls,

SHERWIN-WILLIAMS **CASENITE**

Washable Kalsomine



THE SHERWIN-WILLIAMS CO.

ADMINISTRATION OFFICES: CLEVELAND, OHIO

SALES OFFICES, FACTORIES AND WAREHOUSES
IN PRINCIPAL CITIES

Printed in U. S. A.

CC363 2-36 588

SHERWIN-WILLIAMS **CASENITE**

Weatherable Kalkamine

Digitized by



ASSOCIATION
FOR
PRESERVATION
TECHNOLOGY,
INTERNATIONAL

www.apti.org

BUILDING
TECHNOLOGY
HERITAGE
LIBRARY

www.archive.org/details/buildingtechnologyheritagelibrary

From the collection of:

Jablonski Building Conservation
www.jbconservation.com